

26000 – 26800 XSL Pigments

A New Group of Pigments which are easily soluble in water

Thanks to a special treatment with dispersing agents. The pigments can easily be stirred into water, and the particles will be perfectly dispersed, similar to color concentrates. The color intensity is reached easily and quickly.

		Lightfastness	Acid	Alkali	Lime
26000	XSL Titanium White, PW 6	8,8,8	5	5	5
26120	XSL Translucent Yellow, PY 42	8,8,8	5	5	5
26140	XSL Translucent Red, PR 101	8,8,8	5	5	5
26308	XSL Poppy Red, PR 112.12370	7,7,6	5	5	5
26310	XSL Irgazine® Red DPP, PR 254.56110	8,8,8	5	5	5
26405	XSL Phthalo Blue, Royal Blue, PB 15:2. 74160	8,8,8	5	5	5
26500	XSL Phthalo Green dark, PG 7	8,8,8	5	5	5
26600	XSL Black, Furnace Black, PBk 7	8,8,8	5	5	5

Aqueous wood stains can be prepared because of its good solubility in water. XSL Pigments are very lightfast, unlike normal stains.

Wood Stains with XSL Pigments

The table below shows how to get a wide range of wood stain colors with XSL pigments:

30 Parts Dispersion K 52 or another acrylic dispersion, e.g. Dispersion K 9 or Plextol D 498
 70 Parts Water
 ... Parts of the pigments listed below

Product Number	C.I.	Pine	Umbrella Pine	Oak	Walnut	Chestnut	Teak	Ash-Tree	Rose Wood	Ebony	Mahogany	Silver-Gray
26120	PY 42.77492	14	8.5	2.7	1.9	-	-	6.9	-	-	-	0.4
26140	PR 101.77491	-	0.2	0.5	1.5	2.5	6.3	0.6	4.6	0.7	6.9	-
26600	PBk 7.77266	-	0.03	0.1	0.2	0.06	0.2	0.3	0.3	1.6	-	1.2
26000	PW 6.77891	-	-	-	-	-	-	-	-	-	-	1.9

26800 SET: XSL Pigments

Contains 100g jars of pigments 26000, 26120, 26140, and 26600, and 20 g jars of pigments 26308, 26310, 26405, and 26500.